

Listing of Claims:

Cancel claims 74 to 77 and 97 to 99, without prejudice.

1. to 59. (Canceled)

60. (Currently Amended) A method for making a web of paper or board comprising:
forming a web from fibers; and

treating a surface of the web with a treatment material comprising pigment particles having an average size in the range of 0.5 to ~~[[500]]~~ 100 nm, wherein the treatment material does not comprise a binder.

61. (Previously Presented) The method of claim 60, wherein the pigment particles have an average size in the range of 15 to 25 nm.

62. (Previously Presented) The method of claim 60, wherein the web is treated with pigment particles that have an average size sufficiently small to bind the particles together at least by van der Waals forces.

63. (Previously Presented) The method of claim 60, wherein the web is treated with calcium carbonate particles (CaCO_3).

64. (Previously Presented) The method of claim 63, wherein the web is treated with particles comprised of single elementary particles.

65. (Previously Presented) The method of claim 63, wherein the web is treated with flocced particles comprised of elementary particles.

66. (Currently Amended) The method of claim 60, wherein the web is treated with flocced aggregates of the pigment particles, the flocced aggregates having an average ~~[[size]]~~ diameter ~~[[not larger than 100]]~~ less than 500 nm.

67. (Previously Presented) The method of claim 65, wherein the treating step comprises creating a turbulent flow of the flocced particles, and wherein a size of the flocced particles is controlled by regulating a degree of turbulence in the turbulent flow.

68. (Previously Presented) The method of claim 66, wherein the treating step comprises creating a turbulent flow of the flocced particles, and wherein a size of the flocced particles is controlled by regulating a degree of turbulence in the turbulent flow.

69. (Previously Presented) The method of claim 65, wherein a size of the flocced particles is controlled by adjusting the pH level of the particle surroundings.

70. (Previously Presented) The method of claim 66, wherein a size of the flocced particles is controlled by adjusting the pH level of the particle surroundings.

71. (Previously Presented) The method of claim 60, wherein said treating step comprises treating the web with slaked lime (CaO), reacting the slaked lime on the web with water to form calcium hydroxide (Ca(OH)_2), and reacting the calcium hydroxide on the web with carbon dioxide (CO_2) to form calcium carbonate particles (CaCO_3).

72. (Previously Presented) The method of claim 60, wherein said treating step comprises treating the web with calcium hydroxide (Ca(OH)_2) and then reacting the calcium hydroxide on the web with carbon dioxide (CO_2) to form calcium carbonate particles (CaCO_3).

73. (Previously Presented) The method of claim 60, wherein a solids content of the treatment material is at least 80 %.

74. (Cancelled)

75. (Cancelled)

76. (Cancelled)

77. (Cancelled)

78. (Previously Presented) The method claim 60, further comprising, before said treating step, one of mechanical and thermomechanical treatment to promote adherence of the particles to the web surface.

79. (Previously Presented) The method of claim 78, wherein the mechanical treatment comprises brushing the web to elevate microfibrils of web fiber walls up from the surface of the web.

80. (Previously Presented) The method of claim 79, wherein material used to brush the web is selected so that the brushed surface of the web is charged with static electricity.

81. (Previously Presented) The method claim 60, further comprising calendering the web after the treating step.

82. (Previously Presented) The method of claim 71, further comprising calendering the web before the calcium carbonate particles are crystallized from an amorphous state.

83. (Previously Presented) The method of claim 72, further comprising calendering the web before the calcium carbonate particles are crystallized from an amorphous state.

84. (Previously Presented) The method of claim 82, wherein at least one heated calender roll is used to calender the web.

85. (Previously Presented) The method of claim 83, wherein at least one heated calender roll is used to calender the web.

86. (Canceled)

87. (Canceled)

1 88. (Previously Presented) A method for forming a paper, board or plant-fiber-based
2 web, comprising:

3 spreading onto a surface of a moving web-formation substrate raw material comprising at
4 least one of the group consisting of cellulosic fiber, plant fiber and other material suitable for
5 manufacturing a paper, a board or a nonwoven product;

6 passing the raw material on the web-formation substrate through at least one compressive
7 nip to form a web from fibers in the raw material;

8 bringing the web-formation substrate to a first electric potential;

9 applying a second electric potential higher than said first electric potential and displaced
10 from said first electric potential at a distance above the surface of the web-formation substrate
11 onto which the raw material has been spread so that an electric field is established between said
12 first and second electric potentials;

13 adjusting a voltage between the first and second electric potentials so that the voltage is
14 sufficient to establish a corona discharge between points where the first and second electric
15 potentials are applied, the corona discharge being capable of causing an ion blast from the
16 second electric potential to the first electric potential so as to transport particulate raw material
17 between the first and second electric potentials onto the web-formation substrate and assure
18 adherence of the raw material to the web-formation substrate; and

19 treating the web with elementary pigment particles having an average size in the range of
20 0.5 to 100 nm, wherein the elementary pigment particles do not comprise a binder and the
21 treating of the web does not employ a binder.

89. (Previously Presented) The method of claim 88, wherein the elementary pigment particles have an average size in the range of 15 to 25 nm.

90. (Canceled)

91. (Previously Presented) The method of claim 88, wherein the elementary pigment particles are added to the surface of the formed web.

92. (Canceled)

93. (Canceled)

94. (Currently Amended) The method of claim [[92]] 91, wherein the elementary pigment particles are added to the surface of the formed web by means of an ion-blast technique.

95. (Previously Presented) The method of claim 88, wherein the web is treated by applying the particles to the web surface by first treating the web with slaked lime (CaO), then reacting the slaked lime with water to form calcium hydroxide (Ca(OH)_2), and then reacting the calcium hydroxide with carbon dioxide (CO_2), whereby calcium carbonate particles (CaCO_3) are formed.

96. (Previously Presented) The method of claim 88, wherein the web is treated by applying the particles to the web surface by first treating the web with calcium hydroxide (Ca(OH)_2), and then reacting the calcium hydroxide with carbon dioxide (CO_2), whereby calcium carbonate particles (CaCO_3) are formed.

97. (Cancelled)

98. (Cancelled)

99. (Cancelled)

100. (Previously Presented) The method of claim 88, further comprising augmenting adherence of the particles of the web treatment material to the web surface by mechanical or thermomechanical treatment.

101. (Previously Presented) The method of claim 100, wherein the web is brushed to elevate microfibrils of the web fiber walls up from the web surface.

102. (Previously Presented) The method of claim 101, wherein the web is brushed with a brush material selected so that the surface of the web after brushing is charged with static electricity of negative or positive polarity as desired.

103. (Previously Presented) The method of claim 88, further comprising calendaring the web after the treating step.

104. (Previously Presented) The method of claim 95, wherein the web is calendered prior to crystallization of the calcium carbonate particles from their amorphous state.

105. (Currently Amended) The method of claim 104, wherein the web is calendered with at least one calender ~~[[rolls]]~~ roll that is heated.

106. (Canceled)

107. (Previously Presented) The method of claim 88, wherein the web is treated with recycled calcium carbonate obtained from precipitated calcium carbonate residue of the deinking process of recycled fiber.

108. (Previously Presented) The method of claim 107, wherein the calcium carbonate is prepared by calcining calcium-carbonate-containing precipitate into lime, reacting the lime with water and reacting the calcium hydroxide thus formed with carbon dioxide in a turbulent gas phase, whereby fine particulate calcium carbonate is formed.